



96837

96830

SPI

Tape is wound on a paper core.

Antistatic Cellulose Tape

For general purpose applications

- 2.4 mil (0.06 mm) total thickness
- Cellulose film construction 10E9 - 10E10 ohms
- Rubber based adhesive absorbs moisture
- Adhesive surface resistivity 10E9 - 10E10 ohms
- Temperature Range 10°C - 50°C (50°F - 122°F); meets MIL-B-81705 of 100°C for 10 min max
- Available in clear

Also available in clear with ESD symbols. Marking is approved symbols of Mil STD-1285*, JEDEC and ESD Association. Symbols printed in between film and adhesive; will not rub off.

*Military organizations sometimes use MIL-STD-1285 for hardware marking and that document once required the use of the "three arrows in a circle" symbol. That symbol has been changed for consistency with industry marking to the "hand in triangle" ESD Susceptibility symbol. (Ref: TR20.20 section 5.3.14.1)



Width


| Tape | 0.5" | .75" | 1" | 2" | Core | Length |
|-----------------------------------------|-------|-------|-------|-------|------|--------|
| Antistatic Clear Cellulose | 96830 | 96831 | 96832 | | 1" | 36 yds |
| | 96833 | 96834 | 96835 | 96836 | 3" | 72 yds |
| Antistatic Clear Cellulose with Symbols | 96837 | 96838 | 96839 | 96840 | 3" | 72 yds |

Width tolerance $\pm 1/32"$

Tape widths are nominal metric ± 0.8 mm ($\pm 1/32"$).

- 1/4" is 6 mm nominal or 0.236"
- 1/2" is 12 mm nominal or 0.472"
- 3/4" is 18 mm nominal or 0.709"
- 1" is 24 mm nominal or 0.945"
- 2" is 48 mm nominal or 1.890"

The user must determine the suitability for use of an antistatic tape for his particular application.



Made in America

No silicone based material (adhesive, film backing, release material) is used in the manufacture of our cellulose tape.

Note: For best results, tape inventory should be continually replenished. It is recommended that rolls of tape be stored flat and rotated (flipped over to the other side) periodically. Tapes should be stored in a dry, well ventilated room with a reasonably consistent temperature of 68°F (20°C) and be protected from exposure to direct sunlight. Tape should not be stored in ultraviolet sunlight, moisture, or heat. See Limited Warranty; SPI expressly warrants that for a period of one (1) year from the date of purchase, our Wescorp Brand Antistatic Tape will be free of defects in material (parts) and workmanship (labor). Tape over one year old should be evaluated by the user to determine acceptability for the user's application.

*Wescorp is a Desco Industries brand.

WESCORP* ANTISTATIC CELLULOSE TAPE ON PAPER CORE

ESD SYSTEMS.com

ESD SYSTEMS.COM
432 NORTHBORO ROAD CENTRAL
MARLBORO, MA 01752 USA
TEL. (508) 485-7390 FAX (508) 480-0257



Visit our online
library of Tech Drawings:
ESDSystems.com

DRAWING NUMBER
96830

DATE:
December
2008